

SECTION 09 65 19 - RESILIENT TILE FLOORING

PART 1 - GENERAL

1.1 SUMMARY

- A. Section Includes:
 - 1. Rubber floor tile.
 - 2. Vinyl composition floor tile.

1.2 SUBMITTALS

- A. Product Data: For each type of product indicated.
- B. LEED Submittals:
 - 1. Product Data for Credit EQ 4.1: For adhesives, including printed statement of VOC content and chemical components.
- C. Shop Drawings: For each type of floor tile. Include floor tile layouts, edges, columns, doorways, enclosing partitions, built-in furniture, cabinets, and cutouts.
- D. Samples: Full-size units of each color and pattern of floor tile required.
- E. Maintenance data.

1.3 QUALITY ASSURANCE

- A. Fire-Test-Response Characteristics: As determined by testing identical products according to ASTM E 648 or NFPA 253 by a qualified testing agency.
 - 1. Critical Radiant Flux Classification: Class I, not less than 0.45 W/sq. cm.

1.4 PROJECT CONDITIONS

- A. Maintain ambient temperatures within range recommended by manufacturer in spaces to receive floor tile.
- B. Until Substantial Completion, maintain ambient temperatures within range recommended by manufacturer.
- C. Close spaces to traffic during floor tile installation.
- D. Close spaces to traffic for 48 hours after floor tile installation.

- E. Install floor tile after other finishing operations, including painting, have been completed.

PART 2 - PRODUCTS

2.1 RUBBER FLOOR TILE

- A. Products: Subject to compliance with requirements, provide the following:
 - 1. Burke Mercer Flooring Products, Division of Burke Industries Inc.; **<Insert product name or designation>**.
 - 2. Endura Rubber Flooring, a division of Burke Industries Inc.; **<Insert product name or designation>**.
 - 3. Flexco; **<Insert product name or designation>**.
 - 4. Johnsonite; **<Insert product name or designation>**.
 - 5. Mondo Rubber International, Inc.; **<Insert product name or designation>**.
 - 6. Nora Rubber Flooring, Freudenberg Building Systems, Inc.; **<Insert product name or designation>**.
 - 7. R.C.A. Rubber Company (The); **<Insert product name or designation>**.
 - 8. Roppe Corporation, USA; **<Insert product name or designation>**.
- B. Tile Standard: ASTM F 1344, Class I-A, homogeneous rubber tile, solid color.
- C. Hardness: Manufacturer's standard hardness.
- D. Wearing Surface: Textured.
- E. Thickness: 0.125 inch.
- F. Size: **[12 by 12 inches] [24 by 24 inches]**.
- G. Colors and Patterns: As indicated by manufacturer's designations.

2.2 VINYL COMPOSITION FLOOR TILE

- A. Products: Subject to compliance with requirements, provide the following:
 - 1. AB ColorPlus, American Biltrite (Canada) Ltd.; **<Insert product name or designation>**.
 - 2. Armstrong World Industries, Inc.; **<Insert product name or designation>**.
 - 3. Congoleum Corporation; **<Insert product name or designation>**.
 - 4. Mannington Mills, Inc.; **<Insert product name or designation>**.
 - 5. Tarkett, Inc.; **<Insert product name or designation>**.
 - 6. Vinylasa Tile, Distributed by American Tile Inc.; **<Insert product name or designation>**.
 - 7. **<Insert manufacturer's name; product name or designation>**.
- B. Tile Standard: ASTM F 1066, Class 2, through-pattern tile.
- C. Wearing Surface: Smooth.

- D. Thickness: 0.125 inch.
- E. Size: 12 by 12 inches.
- F. Colors and Patterns: As indicated by manufacturer's designations.

2.3 INSTALLATION MATERIALS

- A. Trowelable Leveling and Patching Compounds: Latex-modified, portland cement based or blended hydraulic-cement-based formulation provided or approved by manufacturer for applications indicated.
- B. Adhesives: Water-resistant type recommended by manufacturer to suit floor tile and substrate conditions indicated.
 - 1. Use adhesives that comply with the following limits for VOC content when calculated according to 40 CFR 59, Subpart D (EPA Method 24):
 - a. Vinyl Composition Floor Tile Adhesives: Not more than 50 g/L.
 - b. Rubber Floor Tile Adhesives: Not more than 60 g/L.
- C. Floor Polish: Provide protective liquid floor polish products as recommended by manufacturer.

PART 3 - EXECUTION

3.1 PREPARATION

- A. Prepare substrates according to manufacturer's written instructions to ensure adhesion of resilient products.
- B. Concrete Substrates: Prepare according to ASTM F 710.
 - 1. Verify that substrates are dry and free of curing compounds, sealers, and hardeners.
 - 2. Remove substrate coatings and other substances that are incompatible with adhesives and that contain soap, wax, oil, or silicone, using mechanical methods recommended by manufacturer. Do not use solvents.
 - 3. Alkalinity and Adhesion Testing: Perform tests recommended by manufacturer. Proceed with installation only after substrates pass testing.
 - 4. Moisture Testing: Perform tests recommended by floor covering manufacturer and as follows. Proceed with installation only after substrates pass testing.
 - a. Perform anhydrous calcium chloride test, ASTM F 1869. Proceed with installation only after substrates have maximum moisture-vapor-emission rate of 3 lb of water/1000 sq. ft. in 24 hours.
 - b. Perform relative humidity test using in situ probes, ASTM F 2170. Proceed with installation only after substrates have a maximum 75% relative humidity level measurement.

- C. Fill cracks, holes, and depressions in substrates with trowelable leveling and patching compound and remove bumps and ridges to produce a uniform and smooth substrate.
- D. Do not install floor tiles until they are same temperature as space where they are to be installed.
 - 1. Move resilient products and installation materials into spaces where they will be installed at least 48 hours in advance of installation.
- E. Sweep and vacuum clean substrates to be covered by resilient products immediately before installation.

3.2 FLOOR TILE INSTALLATION

- A. Comply with manufacturer's written instructions for installing floor tile.
- B. Lay out floor tiles from center marks established with principal walls, discounting minor offsets, so tiles at opposite edges of room are of equal width. Adjust as necessary to avoid using cut widths that equal less than one-half tile at perimeter.
 - 1. Lay tiles square with room axis.
- C. Match floor tiles for color and pattern by selecting tiles from cartons in the same sequence as manufactured and packaged, if so numbered. Discard broken, cracked, chipped, or deformed tiles.
 - 1. Lay tiles with grain running in one direction.
- D. Scribe, cut, and fit floor tiles to butt neatly and tightly to vertical surfaces and permanent fixtures including built-in furniture, cabinets, pipes, outlets, and door frames.
- E. Extend floor tiles into toe spaces, door reveals, closets, and similar openings. Extend floor tiles to center of door openings.
- F. Maintain reference markers, holes, and openings that are in place or marked for future cutting by repeating on floor tiles as marked on substrates. Use chalk or other nonpermanent, nonstaining marking device.
- G. Adhere floor tiles to flooring substrates using a full spread of adhesive applied to substrate to produce a completed installation without open cracks, voids, raising and puckering at joints, telegraphing of adhesive spreader marks, and other surface imperfections.

3.3 CLEANING AND PROTECTION

- A. Comply with manufacturer's written instructions for cleaning and protection of floor tile.
- B. Floor Polish: Remove soil, visible adhesive, and surface blemishes from floor tile surfaces before applying liquid floor polish.
 - 1. Apply two coat(s).

- C. Cover floor tile until Substantial Completion.

END OF SECTION 09 65 19