

## SECTION 06 10 53 - MISCELLANEOUS ROUGH CARPENTRY

### PART 1 - GENERAL

#### 1.1 SUMMARY

- A. This Section includes the following:
  - 1. Framing with dimension lumber.
  - 2. Rooftop equipment bases and support curbs.
  - 3. Wood blocking, cants, and nailers.
  - 4. Wood furring and grounds.
  - 5. Wood sleepers.
  - 6. Plywood backing panels.

#### 1.2 SUBMITTALS

- A. Product Data: For each type of process and factory-fabricated product.
  - 1. Include data for wood-preservative and fire-retardant treatment from chemical treatment manufacturer and certification by treating plant that treated materials comply with requirements.
- B. Research/Evaluation Reports: For the following, showing compliance with building code in effect for Project:
  - 1. Preservative-treated wood.
  - 2. Fire-retardant-treated wood.
  - 3. Power-driven fasteners.

#### 1.3 QUALITY ASSURANCE

- A. Forest Certification: For the following wood products, provide materials produced from wood obtained from forests certified by an FSC-accredited certification body to comply with FSC 1.2, "Principles and Criteria":
  - 1. Dimension lumber framing.
  - 2. Miscellaneous lumber.
  - 3. Exterior wood trim.

## PART 2 - PRODUCTS

### 2.1 WOOD PRODUCTS, GENERAL

- A. Lumber: DOC PS 20 and applicable rules of grading agencies indicated. If no grading agency is indicated, provide lumber that complies with the applicable rules of any rules-writing agency certified by the ALSC Board of Review. Provide lumber graded by an agency certified by the ALSC Board of Review to inspect and grade lumber under the rules indicated.
  - 1. Factory mark each piece of lumber with grade stamp of grading agency.
  - 2. For exposed lumber indicated to receive a stained or natural finish, mark grade stamp on end or back of each piece.
  - 3. Provide dressed lumber, S4S, unless otherwise indicated.
  - 4. Plywood, exterior grade

### 2.2 WOOD-PRESERVATIVE-TREATED MATERIALS

- A. Preservative Treatment by Pressure Process: AWWPA C2, except that lumber that is not in contact with the ground and is continuously protected from liquid water may be treated according to AWWPA C31 with inorganic boron (SBX).
  - 1. Preservative Chemicals: Acceptable to authorities having jurisdiction and containing no arsenic or chromium.
- B. Kiln-dry lumber after treatment to a maximum moisture content of 19 percent. Do not use material that is warped or does not comply with requirements for untreated material.
- C. Mark lumber with treatment quality mark of an inspection agency approved by the ALSC Board of Review.
- D. Application: Treat the following items.
  - 1. Wood cants, nailers, curbs, equipment support bases, blocking, stripping, and similar members in connection with roofing, flashing, vapor barriers, and waterproofing.
  - 2. Wood sills, sleepers, blocking, furring, stripping, and similar concealed members in contact with masonry or concrete.
  - 3. Wood framing and furring attached directly to the interior of below-grade exterior masonry or concrete walls.
  - 4. Wood framing members that are less than 18 inches above the ground in crawl spaces or unexcavated areas.
  - 5. Wood floor plates that are installed over concrete slabs-on-grade.

### 2.3 FIRE-RETARDANT-TREATED MATERIALS

- A. General: Comply with performance requirements in AWWPA C20 (lumber) and AWWPA C27 (plywood).
  - 1. Use Exterior type for exterior locations and where indicated.

2. Use Interior Type A, unless otherwise indicated.
- B. Identify fire-retardant-treated wood with appropriate classification marking of testing and inspecting agency acceptable to authorities having jurisdiction.
- C. Application: Treat all wood on the project, with the exception of the items listed in paragraph above for preservative treatment.
  1. Framing for raised platforms.
  2. Concealed blocking.
  3. Roof construction.
  4. Plywood backing panels.

## 2.4 DIMENSION LUMBER FRAMING

- A. Maximum Moisture Content: 19 percent.
- B. Non-Load-Bearing Interior Partitions: Construction or No. 2 grade of any listed species.
- C. Other Framing: No. 2 grade and any of the following species:
  1. Douglas fir-larch; WCLIB or WWPA.
  2. Douglas fir-south; WWPA.
  3. Hem-fir; WCLIB or WWPA.
- D. Schedule of materials:
  1. Wood studs: Douglas fir-Larch, stud grade
  2. Wood joints: Douglas fir-Larch, No. 1 grade
  3. Wood beams, stringers and posts: Douglas fir-Larch, select structural grade
  4. Plywood sheathing: APA rated sheathing, Exposure 1
  5. Communication backboards: APA A-C Group 1, Exterior,  $\frac{3}{4}$ " thickness

## 2.5 MISCELLANEOUS LUMBER

- A. General: Provide miscellaneous lumber indicated and lumber for support or attachment of other construction, including the following:
  1. Blocking.
  2. Nailers.
  3. Rooftop equipment bases and support curbs.
  4. Cants.
  5. Furring.
  6. Grounds.
  7. Utility shelving.
- B. For items of dimension lumber size, provide Construction or No. 2 grade lumber with 19 percent maximum moisture content of any species.
- C. For exposed boards, provide lumber with 15 percent maximum moisture content of Premium or 2 Common (Sterling) grade; WCLIB, or WWPA.

- D. For concealed boards, provide lumber with 15 percent maximum moisture content and any of the following species and grades:
  - 1. Western woods, Construction or No. 2 Common grade; WCLIB or WWP.

## 2.6 PLYWOOD BACKING PANELS

- A. Telephone and Electrical Equipment Backing Panels: DOC PS 1, Exposure 1, A-C Plugged, fire-retardant treated, in thickness indicated or, if not indicated, not less than 3/4-inch nominal thickness.

## 2.7 FASTENERS

- A. General: Where carpentry is exposed to weather, in ground contact, pressure-preservative treated, or in area of high relative humidity, provide fasteners of Type 304 stainless steel.
- B. Power-Driven Fasteners: NES NER-272.
- C. Screws for Fastening to Cold-Formed Metal Framing: ASTM C 954, except with wafer heads and reamer wings, length as recommended by screw manufacturer for material being fastened.
- D. Machine bolts: ASTM A307
- E. Lag Bolts: Federal Specifications FF-B-561
- F. Nails: common; use galvanized at exterior or wet locations
- G. Gage metal framing connectors: Simpson Strong Tie with ICBO Certification.
- H. Metal Plate connected wood trusses: designed per Truss Plate Institute. (TPI)

## PART 3 - EXECUTION

### 3.1 INSTALLATION, GENERAL

- A. Set carpentry to required levels and lines, with members plumb, true to line, cut, and fitted. Fit carpentry to other construction; scribe and cope as needed for accurate fit. Locate furring, nailers, blocking, grounds, and similar supports to comply with requirements for attaching other construction.
- B. Framing Standard: Comply with AF&PA's "Details for Conventional Wood Frame Construction," unless otherwise indicated.
- C. Do not splice structural members between supports, unless otherwise indicated.
- D. Comply with AWWA M4 for applying field treatment to cut surfaces of preservative-treated lumber.

- E. Securely attach carpentry work to substrate by anchoring and fastening as indicated, complying with the following:
  - 1. NES NER-272 for power-driven fasteners.
  - 2. Table 2304.9.1, "Fastening Schedule," in ICC's International Building Code.
- F. Exterior Wood Trim Installation: Install with minimum number of joints practical, using full-length pieces from maximum lengths of lumber available. Cope at returns and miter at corners to produce tight-fitting joints with full-surface contact throughout length of joint. Use scarf joints for end-to-end joints.
  - 1. Match color and grain pattern across joints.
  - 2. Install to tolerance of 1/8 inch in 96 inches for level and plumb. Install adjoining finish carpentry with 1/32-inch maximum offset for flush installation and 1/16-inch maximum offset for reveal installation.
  - 3. Glue all floor sheathing with minimum continuous bead of carpenter adhesive. Use two continuous beads at abutting panels.

### 3.2 PROTECTION

- A. Protect wood that has been treated with inorganic boron (SBX) from weather. If, despite protection, inorganic boron-treated wood becomes wet, apply EPA-registered borate treatment. Apply borate solution by spraying to comply with EPA-registered label.

**END OF SECTION 06 10 53**